

Wr.Nr.	DIN	ČSN	EN
2.0040	OF-Cu	Cu 99,95	Cu-OF
2.0060	E-Cu 58 (57)	Cu 99,9E	Cu-ETP
-	-	Cu 99,95	-
2.0090	SF-Cu	Cu 99,85	Cu-DHP
-	-	Cu 99,75	-
-	-	Cu 99,5	-
-	-	Cu 99,2 As	-

SLITINY MĚDI TVÁŘENÉ - Převodní tabulka Wr.Nr. - DIN - ČSN - EN

Wr.Nr.	DIN	ČSN	EN
-	-	CuSn	-
-	-	CuSn4	-
-	CuSn6	CuSn6	CuSn6
-	CuSn8	CuSn8	CuSn8
-	-	CuCd 0,2	-
-	CuAl5As	CuAl5	CuAl5As
-	CuAl9Mn2	CuAl9Mn2	-
-	CuAl8Fe3	CuAl9Fe3	CuAl8Fe3
-	CuAl10Fe3Mn2	CuAl10Fe3Mn1,5	CuAl10Fe3Mn2
-	CuAl10Ni5Fe4	CuAl10Fe4Ni4	CuAl10Ni5Fe4
-	-	CuAl9Ni5Fe1Mn1	-
-	-	CuSi3Mn	CuSi3Mn
-	CuNi2Si	CuNi2Si	CuNi2Si
-	-	CuMn13Ni	-
-	-	CuCd1	-
-	CuNi30Mn1Fe	CuNi30FeMn	CuNi30Mn1Fe
-	CuNi30Mn	CuNi30Mn2	-
-	CuNi44Mn1	CuNi45Mn2	-
-	CuZn5	CuZn4	CuZn5
-	CuZn10	CuZn10	CuZn10
-	CuZn15	CuZn15	CuZn15
-	CuZn20	CuZn20	CuZn20
-	CuZn30	CuZn30	CuZn30
-	CuZn33	CuZn33	CuZn33
-	CuZn37	CuZn37	CuZn37
-	CuZn36Pb1,5	CuZn36Pb1	CuZn35Pb2
-	CuZn40	CuZn40	CuZn40
-	CuZn38Pb0,5	CuZn38Pb	CuZn38Pb0,5
-	CuZn38Pb1,5	CuZn39Pb1	CuZn38Pb1 (2)
-	CuZn40Pb2	CuZn39Pb2 (40)	CuZn39Pb2 (40)
-	-	CuZn45Pb3Mn3Fe	-
-	CuZn40Al1	CuZn40Mn3Al1	CuZn39Mn1AlPbSi
-	CuZn40Mn2	CuZn40Mn	CuZn40Mn2Fe1
-	CuZn38Sn1	CuZn38Sn1	CuZn38Sn1As
-	-	CuZn38SnMnAs	-
-	-	CuZn28AlSnMn	CuZn40Mn2Fe1
-	CuNi12Zn24	CuNi15Zn21	CuNi12Zn24